

AX-THERM vs AX-GASKET

Comparison Chart



Properties

	Ax-Therm Muscovite	Ax-Therm Phlogopite	Ax-Gasket Muscovite	Ax-Gasket Phlogopite
Mica Content (IEC 60371-2)	85-90%	85-90%	92%	92%
Silicone Binder Content (IEC 60371-2)	10-15%	10-15%	8%	8%
Density (IEC 60371-2)	2.2-2.3g/cm ³	2.2-2.3g/cm ³	1.8-1.9 g/cm ³	1.8-1.9g/cm ³
Heat Resistance				
Continuous Service	500°C	700°C	500°C	700°C
Intermittent Service	800°C	1000°C	800°C	1000°C
Compressive Strength (ISO 604)				
20°C	400MPa	330MPa		
200°C	250MPa	240MPa		
Flexural Strength	33350psi	24650psi	-	-
Tensile Strength (ISO 527)	150 N/mm ²	100 N/mm ²	140-150 N/mm ²	100-110 N/mm ²
Weight Loss (Continuous Heating 500°C & 700°C)	< 1%	< 1-2%		
Thermal Conductivity (W/m.K)	0.3	0.3	0.3	0.3
Bending Strength (ISO 178)	230 MPa	170 MPa	230 MPa	170 MPa
Water Absorption (ISO 62)	<1%(24h/23°C)	<1%(24h/23°C)	<1% (24h/23°C)	<1% (24h/23°C)
Dielectric Strength: (IEC 60243) - 20°C	25 kV/mm	25 kV/mm	>20 kV/mm	>20 kV/mm
Insulation Resistance - 20°C	10 ¹⁶ Ohms/cm	10 ¹⁶ Ohms/cm		
Volume Resistivity: (IEC 60093)				
23°C	> 10 ¹⁶ B/cm	> 10 ¹⁶ B/cm	> 10 ¹⁷ B/cm	> 10 ¹⁷ B/cm
550 °C	>10 ⁹ B/cm	>10 ⁹ B/cm	>10 ¹² B/cm	>10 ¹² B/cm
Heat Loss: (IEC 60371-2)				
500°C	<1%	<1%	<1%	<1%
700°C		<2%		<2%
Thermal Expansion:				
Perpendicular	100 x 10 ⁻⁶ /°K	100 x 10 ⁻⁶ /°K	60 / 10-6/K	60 / 10-6/K
Parallel	10 x 10 ⁻⁶ /°K	10 x 10 ⁻⁶ /°K	10 / 10-6/K	10 / 10-6/K



32 Gazza Blvd., Farmingdale, NY 11735

Tel: (516) 248-0045 Fax: (516) 706-4949 info@aximmica.com www.aximmica.com

The information contained herein is believed to be accurate and reliable; however Axim Mica cannot be aware of all the applications to which its products may be put, or control the subsequent processing, therefore, Axim Mica cannot make warranties conforming the fitness or suitability for a particular use or purpose. Any proposed application of Axim Mica's products should be thoroughly tested and satisfactory performance independently confirmed by the user.